

Product Data sheet: BG-LL 22B01

<i>Linear low Density PE</i>	<i>Film</i>	
LLDPE: BG-LL 22B01	Density: 0.920 - 0.924	MFI: 0.8 - 1.2
Feature: <ul style="list-style-type: none"> • Comonomer:butane-1(c4) • High stiffness films 	Application: <ul style="list-style-type: none"> • High stiffness blown film • Blending • Lamination 	Additives: <ul style="list-style-type: none"> • Acid scavenger • Antioxidants • Anti-block and Slip agent (on customer request) • Lubricant • Processing aid

Material properties (this data are typical values and shall not be construed as product specifications.)

Resin properties	unit	condition	Typical value	Test method
Melt index	g/10 min	190°c/2.16 kg	0.8-1.2	ASTM D1238
Density	g/l	23°c	0.920-0.924	ASTM D1505
F/E Ratio	-		<30	ASTM D1238
Yellowness Index	-		0.5	ASTM D1925
Ti content	Ppm wt		2	MTM 15636
Fish Eyes	Gels/m ²	-	60	MTM 17108
Haze	%		25	ASTM D1003
Gloss 45°	%O		35	MTM 1702
Dart impact	g		75	ASTM D1709/A
Tensile modulus	2% sec	MD	150	ASTM D882
	Mpa	TD	180	ASTM D882
Tensile strength	Ultimate	MD	49	ASTM D882
	Mpa	TD	43	ASTM D882
Elongation	At braek	MD	800	ASTM D882
	%	TD	900	ASTM D882
Elmendorf tear	g	MD	120	ASTM D1922
		TD	400	ASTM D1922

Aydin Cure

Zafer Mah. 185. Sokak B1 Blok No:4B K:39 D:514 Esenyurt / İSTANBUL Tel: +90 212 876 89 69

Avçılar V.D.: 147 072 63 73 Mersis No: 0147072637300001

www.AydinCure.com

info@AydinCure.com