

## Product Data sheet: BG-LL 22B02

Linear low Density PE	Film	
LLDPE: BG-LL 22B02	Density: 0.920 - 0.924	MFI: 1.8 - 2.2
<b>Feature:</b> <ul style="list-style-type: none"> <li>Comonomer:butane-1(c4)</li> <li>High stiffness films</li> </ul>	<b>Application:</b> <ul style="list-style-type: none"> <li>High stiffness blown and cast film</li> <li>Blending</li> <li>Lamination</li> </ul>	<b>Additives:</b> <ul style="list-style-type: none"> <li>Acid scavenger</li> <li>Antioxidants</li> <li>Anti-block and Slip agent (on customer request)</li> <li>Lubricant</li> </ul>

*Material properties (this data are typical values and shall not be construed as product specifications.)*

Resin properties	unit	condition	Typical value	Test method
Melt index	g/10 min	190°c/2.16 kg	1.8-2.2	ASTM D1238
Density	g/l	23°c	0.920-0.924	ASTM D1505
F/E Ratio	-		<30	ASTM D1238
Yellowness index	-		0.5	ASTM D1925
Ti content	Ppm wt		2	MTM 15636
Fish Eyes	Gels/m <sup>2</sup>	-	60	MTM 17108
Haze	%		13	ASTM D1003
Gloss	%O		90	ASTM D2457
Dart impact	gr		60	ASTM D1709
Tensile strength@Yield	Mpa	TD	13	ASTM D882
	Mpa	MD	12	ASTM D882
Tensile strength@Break	Mpa	TD	38	ASTM D882
	Mpa	MD	40	ASTM D882
Elongation@Break	%	TD	1000	ASTM D882
	%	MD	850	ASTM D882

Aydin Cure

Zafer Mah. 185. Sokak B1 Blok No:4B K:39 D:514 Esenyurt / İSTANBUL Tel: +90 212 876 89 69

Avçılar V.D.: 147 072 63 73

Mersis No: 0147072637300001

[www.AydinCure.com](http://www.AydinCure.com)

[info@AydinCure.com](mailto:info@AydinCure.com)