

Product Data sheet: BG-HD 62N07(UV)

High Density Polyethylene	Injection Molding	
HDPE: BG-HD 62N07	Density: 0.960 - 0.964	MFI: 6 - 8
Feature: <ul style="list-style-type: none"> • Good impact strength • Easy processing • High rigidity • Uv resistant 	Application: <ul style="list-style-type: none"> • Crates • Pallets • Seats • House holdware 	Additives: <ul style="list-style-type: none"> • Acid scavenger • Antioxidants • Lubricant • Uv stabilizer

Material properties (this data are typical values and shall not be construed as product specifications.)

Resin properties	unit	condition	Typical value	Test method
Melt flow index	g/10 min	190°C/2.16 kg	6-8	ASTM D1238
Density	g/cc	23°C	0.960-0.964	ASTM D1505
Physical properties	unit		Typical value	Test method
F/E Ratio	-		<30	ASTM D1925
Yellow Index	-		0.5	ASTM D1238
Ti content	ppm wt		2	Internal 15636
Flexural Modulus	Mpa		1500	ASTM D790
Notched Izod impact	(j/m)	23°C	55	ASTM D256/A

*All above mentioned data are typical values and not to be construed as real specification. Users should confirm results by their own tests. For more information about guaranteed items, please refer to S.S.S. (standard sales specifications) .

*F/E : Ratio of MIF (190°C/21.6Kg) / M IE (190°C/2.16Kg)

Aydin Cure

Zafer Mah. 185. Sokak B1 Blok No:4B K:39 D:514 Esenyurt / İSTANBUL Tel: +90 212 876 89 69

Avçılar V.D.: 147 072 63 73

Mersis No: 0147072637300001

www.AydinCure.com

info@AydinCure.com